

Viapol Systema 4

CE

Description : elastoplastic polymer bitumen membrane BPP, compound in distilled bitumen modified with high molecular weight polymer, reinforced with nonwoven polyester fabric, glass stabilized

Field of Application : top layer in a multi-layer waterproofing system - base or intermediate layer in a multi-layer waterproofing system - below grade foundations and walls

Method of Application : torched-on

Applicable Directive : EN 13707 - EN 13969

Dangerous Substances : the product does not contain dangerous substances (D.L 152/06)

CHARACTERISTIC	EN DRC	UNIT	VALUE		TOL
Visible Defects	EN 1850-1	-----	pass		-----
Thickness	EN 1849-1	mm	4,0		-10%
Areic Mass	EN 1849-1	kg/m ²			npd
Width and Length	EN 1848-1	m	1,00	10,00	-1%
Straightness	EN 1848-1	mm	max 20		pass
Max Tensile Force (L / T)	EN 12311-1	N/5cm	500	350	-20%
Elongation (L / T)	EN 12311-1	%	40	40	-15 abs
Resistance to Tearing (L / T)	EN 12310-1	N/5cm	140	160	pass
Resistance to Static Loading	EN 12730-A	kg	15		pass
Resistance to Impact	EN 12691	mm	700		pass
Joint Strength (L / T)	EN 12317-1	N/5cm			npd
Peel Resistance of Joint	EN 12316-1	N/5cm			npd
Pliability (Cold Flexibility)	EN 1109	°C	-5		pass
Pliability (Aged)	EN 1296	°C			npd
Uv Ageing (Visible Defects)	EN 1297	-----	pass		-----
Watertightness	EN 1928	kPa	60		pass
Water Vapour Permeability	EN 1931	μ x 1.000	20 (default)		npd
Water Vapour Permeability (Aged)	EN 1296	μ x 1.000			npd
Form Stability (New / Aged)	EN 1110	°C	120	120	pass
Dimensional Stability (L / T)	EN 1107-1	%	-0,25	+0,15	pass
Root Resistance	MBP Group	% add			npd
External Fire Performance	EN 13501-5	class	F(roof)		npd
Reaction to Fire	EN 13505-1	class	F		npd
Adhesion of Granules (Mineral Version)	EN 12039	%			npd

Standard	Thickness	mm	2	3	4	5
	Rolls x Pallet	n°	-----	30	23	20
Mineral	Areic Mass	kg/m ²	3,5	4,0	4,5	5,0
	Rolls x Pallet	n°	-----	-----	-----	-----
Upper Finishing	anti-adherent dotted talc					
Lower Finishing	thermo-fusible polyethylene film					
Packaging	shrinkable polyethylene film, on pallet					
Additional Info	" Polymer Bitumen Membrane Info Sheet ", current release					

technical data declared may vary without previous notice

rev 000 - 04.2008

vetroasfalto

Vetroasfalto SpA
Via Pascoli, 3 - 20060 Basiglio (MI) - Italy
tel +39.02.959831 - fax +39.02.95983555
email: vetroasfalto@vetroasfalto.com
www.vetroasfalto.com
Quality Assurance : UNI EN ISO 9001:2000
Certificate : 1773/CPD-11/001

