

Viapol Syntesi SB 160 Mineral CE

Description : elastoplastomeric polymer bitumen membrane BPP, compound in distilled bitumen modified with high molecular weight polymer, reinforced with nonwoven spunbond polyester fabric, glass stabilized, top face coated with hot-bonded slate granules

Field of Application : top layer, self protected, in a multi-layer waterproofing system

Method of Application : torched-on

Applicable Directive : EN 13707

Dangerous Substances : the product does not contain dangerous substances (D.L 152/06)

CHARACTERISTIC	EN DRC	UNIT	VALUE		TOL
Visible Defects	EN 1850-1	-----	pass		-----
Thickness	EN 1849-1	mm			npd
Areic Mass	EN 1849-1	kg/m ²	4,5		-10%
Widht and Length	EN 1848-1	m	1,00	10,00	-1%
Straightness	EN 1848-1	mm	max 20		pass
Max Tensile Force (L / T)	EN 12311-1	N/5cm	800	550	-20%
Elongation (L / T)	EN 12311-1	%	45	45	-15 abs
Resistance to Tearing (L / T)	EN 12310-1	N/5cm	160	160	pass
Resistance to Static Loading	EN 12730-A	kg	15		pass
Resistance to Impact	EN 12691	mm	900		pass
Joint Strenght (L / T)	EN 12317-1	N/5cm			npd
Peel Resistance of Joint	EN 12316-1	N/5cm			npd
Pliability (Cold Flexibility)	EN 1109	°C	-10		pass
Pliability (Aged)	EN 1296	°C			npd
Uv Ageing (Visible Defects)	EN 1297	-----	pass		npd
Watertightness	EN 1928	kPa	60		pass
Water Vapour Permeability	EN 1931	μ x 1.000	20 (default)		npd
Water Vapour Permeability (Aged)	EN 1296	μ x 1.000			npd
Form Stability (New / Aged)	EN 1110	°C	120	120	pass
Dimensional Stability (L / T)	EN 1107-1	%	-0,5	+0,5	pass
Root Resistance	MBP Group	% add			npd
External Fire Performance	EN 13501-5	class	F(roof)		npd
Reaction to Fire	EN 13505-1	class	F		npd
Adhesion of Granules (Mineral Version)	EN 12039	%	≤ 30		pass

Standard	Thickness	mm	2	3	4	5
	Rolls x Pallet	n°	-----	-----	-----	-----
Mineral	Areic Mass	kg/m ²	3,5	4,0	4,5	5,0
	Rolls x Pallet	n°	-----	25	25	20
Upper Finishing	slate chips/granules (mineral self-protection)					
Lower Finishing	thermo-fusible polyethylene film					
Packaging	shrinkable polyethylene film, on pallet					
Additional Info	" Polymer Bitumen Membrane Info Sheet ", current release					

technical data declared may vary without previous notice

rev 000 - 04.2008



Vetroasfalto SpA
 Via Pascoli, 3 - 20060 Basiano (MI) - Italy
 tel +39.02.959831 - fax +39.02.9598355
 email: vetroasfalto@vetroasfalto.com
 www.vetroasfalto.com
 Quality Assurance : UNI EN ISO 9001:200C
 Certificate : 1773/CPD-11/001

