

Viapol Syntesi RAD 4

Description : elastoplastomeric polymer bitumen membrane BPP, compound in distilled bitumen modified with high molecular weight polymer, reinforced with nonwoven spunbond polyeste fabric, glass stabilized. The bituminous compound is added with a specific and permanent anti-root additive (Preventol B2® by Bayer)

Field of Application : top layer, root-resistant, in a multy-layer waterproofing system - below grade, root-resistant, in foundations and walls

Method of Application : torched-on

Applicable Directive : EN 13707 - EN 13969

Dangerous Substances : the product does not contain dangerous substances (D.L 152/06)

CARATTERISTICA	NORMA EN	U.M	VALORE		TOLL
Visible Defects	EN 1850-1	-----	pass		-----
Thickness	EN 1849-1	mm	4,0		-0,2
Areic Mass	EN 1849-1	kg/m ²			npd
Widht and Length	EN 1848-1	m	1,00	10,00	-1%
Straightness	EN 1848-1	mm	max 20		supera
Max Tensile Force (L / T)	EN 12311-1	N/5cm	600	400	-20%
Elongation (L / T)	EN 12311-1	%	40	40	-15 abs
Resistance to Tearing (L / T)	EN 12310-1	N/5cm	140	140	supera
Resistance to Static Loading	EN 12730-A	kg	15		supera
Resistance to Impact	EN 12691	mm	800		supera
Joint Strenght (L / T)	EN 12317-1	N/5cm			npd
Peel Resistance of Joint	EN 12316-1	N/5cm			npd
Pliability (Cold Flexibility)	EN 1109	°C	-10		supera
Pliability (Aged)	EN 1296	°C			npd
Uv Ageing (Visible Defects)	EN 1297	-----	pass		-----
Watertightness	EN 1928	kPa	60		supera
Water Vapour Permeability	EN 1931	μ x 1.000	20 (default)		npd
Water Vapour Permeability (Aged)	EN 1296	μ x 1.000			npd
Form Stability (New / Aged)	EN 1110	°C	120		supera
Dimensional Stability (L / T)	EN 1107-1	%	-0,25	+0,15	supera
Root Resistance	MBP Group	% add	≥ 0,5		supera
External Fire Performance	EN 13501-5	class	F(roof)		npd
Reaction to Fire	EN 13505-1	class	F		npd
Adhesion of Granules (Mineral Version)	EN 12039	%			npd

Standard	Thickness	mm	2	3	4	5
	Rolls x Pallet	n°	-----	-----	23	20
Mineral	Areic Mass	kg/m ²	3,5	4,0	4,5	5,0
	Rolls x Pallet	n°	-----	-----	-----	-----
Upper Finishing	anti-adherent dotted talc					
Lower Finishing	thermo-fusible polyethylene film					
Packaging	shrinkable polyethylene film, on pallet					
Additional Info	" Polymer Bitumen Membrane Info Sheet ", current release					

technical data declared may vary without previous notice

rev 000 - 04.2008



Vetroasfalto SpA
 Via Pascoli, 3 - 20060 Basiano (MI) - Italy
 tel +39.02.959831 - fax +39.02.95983555
 email: vetroasfalto@vetroasfalto.com
 www.vetroasfalto.com
 Quality Assurance : UNI EN ISO 9001:2000
 Certificate : 1773/CPD-11/001

