

# Viapol Winflex Polyester 45 Mineral $\text{CE}$

**Description** : elastomeric polymer bitumen membrane BPE, compound in distilled bitumen modified with high molecular weight polymer, reinforced with nonwoven polyester fabric, top face coated with hot-bonded slate granules

**Field of Application** : top layer, self protected, in a multi-layer waterproofing system

**Method of Application** : torched-on

**Applicable Directive** : EN 13707

**Dangerous Substances** : the product does not contain dangerous substances ( D.L 152/06 )

CHARACTERISTIC	EN DRC	UNIT	VALUE		TOL
Visible Defects	EN 1850-1	-----	pass		-----
Thickness	EN 1849-1	mm			npd
Areic Mass	EN 1849-1	kg/m <sup>2</sup>	4,5		-10%
Widht and Length	EN 1848-1	m	1,00	10,00	-1%
Straightness	EN 1848-1	mm	max 20		pass
Max Tensile Force ( L / T )	EN 12311-1	N/5cm	900	700	-20%
Elongation ( L / T )	EN 12311-1	%	50	50	-15 abs
Resistance to Tearing ( L / T )	EN 12310-1	N/5cm	170	170	pass
Resistance to Static Loading	EN 12730-A	kg	20		pass
Resistance to Impact	EN 12691	mm	1.000		pass
Joint Strenght ( L / T )	EN 12317-1	N/5cm			npd
Peel Resistance of Joint	EN 12316-1	N/5cm			npd
Pliability ( Cold Flexibility )	EN 1109	°C	-20		pass
Pliability ( Aged )	EN 1296	°C			npd
Uv Ageing ( Visible Defects )	EN 1297	-----	pass		-----
Watertightness	EN 1928	kPa	60		pass
Water Vapour Permeability	EN 1931	$\mu \times 1.000$	20 ( default )		npd
Water Vapour Permeability ( Aged )	EN 1296	$\mu \times 1.000$			npd
Form Stability ( New / Aged )	EN 1110	°C	100		pass
Dimensional Stability ( L / T )	EN 1107-1	%	-0,5	+0,5	pass
Root Resistance	MBP Group	% add			npd
External Fire Performance	EN 13501-5	class	F(roof)		npd
Reaction to Fire	EN 13505-1	class	F		npd
Adhesion of Granules ( Mineral Version )	EN 12039	%	$\leq 30$		pass

Standard	Thickness	mm	2	3	4	5
	Rolls x Pallet	n°	-----	-----	-----	-----
Mineral	Areic Mass	kg/m <sup>2</sup>	3,5	4,0	4,5	5,0
	Rolls x Pallet	n°	-----	25	25	20
Upper Finishing	slate chips/granules ( mineral self-protection )					
Lower Finishing	thermo-fusible polyethylene / polypropyhylene film					
Packaging	shrinkable polyetylene film, on pallet					
Additional Info	" Polymer Bitumen Membrane Info Sheet ", current release					

technical data declared may vary without previous notice

rev 000 - 04.2008



Vetroasfalto SpA  
 Via Pascoli, 3 - 20060 Basiano ( MI ) - Italy  
 tel +39.02.959831 - fax +39.02.95983555  
 email: vetroasfalto@vetroasfalto.com  
 www.vetroasfalto.com  
 Quality Assurance : UNI EN ISO 9001:2000  
 Certificate : 1773/CPD-11/001

