

# Phase Fiberglass



**Description** : elastomeric, **thermo-adhesive**, polymer bitumen membrane BPE, compound in distilled bitumen modified with high molecular weight polymer, reinforced with glass fibre mat. The particular polymeric blend used offers great thermo-adhesive characteristics

**Field of Application** : base or intermediate layer in a multy-layer waterproofing system - water vapour retarder layer

**Method of Application** : upperside torching-on

**Applicable Directive** : EN 13707

**Dangerous Substances** : the product does not contain dangerous substances ( D.L 152/06 )

CHARACTERISTIC	EN DRC	UNIT	VALUE		TOL
Visible Defects	EN 1850-1	-----	pass		-----
Thickness	EN 1849-1	mm	3,0		-10%
Areic Mass	EN 1849-1	kg/m <sup>2</sup>			npd
Widht and Length	EN 1848-1	m	1,00	10,00	-1%
Straightness	EN 1848-1	mm	max 20		pass
Max Tensile Force ( L / T )	EN 12311-1	N/5cm	350	200	-20%
Elongation ( L / T )	EN 12311-1	%	2	2	-2 abs
Resistance to Tearing ( L / T )	EN 12310-1	N/5cm	80	80	pass
Resistance to Static Loading	EN 12730-A	kg	5		pass
Resistance to Impact	EN 12691	mm	500		pass
Joint Strenght ( L / T )	EN 12317-1	N/5cm			npd
Peel Resistance of Joint	EN 12316-1	N/5cm			npd
Pliability ( Cold Flexibility )	EN 1109	°C	-25		pass
Pliability ( Aged )	EN 1296	°C			npd
Uv Ageing ( Visible Defects )	EN 1297	-----			npd
Watertightness	EN 1928	kPa	60		pass
Water Vapour Permeability	EN 1931	μ x 1.000	20 ( default )		npd
Water Vapour Permeability ( Aged )	EN 1296	μ x 1.000			npd
Form Stability ( New / Aged )	EN 1110	°C	100	100	pass
Dimensional Stability ( L / T )	EN 1107-1	%	n.a	n.a	pass
Root Resistance	MBP Group	% add			npd
External Fire Performance	EN 13501-5	class	F(roof)		npd
Reaction to Fire	EN 13505-1	class	F		npd
Adhesion of Granules ( Mineral Version )	EN 12039	%			npd

Standard	Thickness	mm	2	3	4	5
	Rolls x Pallet	n°	25	30	25	-----
Mineral	Areic Mass	kg/m <sup>2</sup>	3,5	4,0	4,5	5,0
	Rolls x Pallet	n°	-----	-----	-----	-----
Upper Finishing	thermo-fusible polyethylene film					
Lower Finishing	anti-adherent polypropylene removable film					
Packaging	shrinkable polyethylene film, on pallet					
Additional Info	" Polymer Bitumen Membrane Info Sheet ", current release					

technical data declared may vary without previous notice

rev 000 - 04.2008



Sappi divisione di Vetroasfalto s.p.a.  
 Export Dept. Via Pascoli, 3 - 20060 - Basiano (MI) ITALY  
 tel +39 02.95769000 - fax +39 02.95760225  
 email: export@sappi.it Web: www.sappi.com  
 Azienda certificata UNI EN ISO 9001:2000  
 Certificazione CE 1773/CPD-11/001